










Fact Sheet: PC ex Automotive

Characteristics	Polycarbonate
 Purity	> 99.9 %
 Colour	Regrind black
 Grain size	< 8 mm
 Residual moisture	< 0.25 %
 Density	1.19 g/m ³
 MFI	13 to 16 g/10min (300 °C and 1.2 kg)
 Regrind	