










Fact Sheet: PS & PC ex MedTech

Characteristics	Polystyrol	Polycarbonate
 Purity	> 99.9 %	> 99.9 %
 Colour	Regrind coloured	Regrind transparent
 Grain size	< 8 mm	< 8 mm
 Residual moisture	< 0.2 %	< 0.2 %
 Density	1.04 g/cm ³	1.18 to 1.19 g/cm ³
 MFI	11 to 13 g/10min (200 °C and 5.0 kg)	13 to 15 g/10min (300 °C and 1.2 kg)
 Regrind	