



# Material data sheet – PP GF20 (C380)

## General technical data

Type of material	PP GF
Description	black recycle
Origin	ex automotive

## Physical/mechanical properties

	Value	Unit	Test method
MFI (230 °C/2.16 kg)	< 29	g/10 min	EN ISO 1133
Ash residue	20	%	EN ISO 1172
Density	1.03	g/cm <sup>3</sup>	EN ISO 1183
Purity	> 99.8	%	DFA, MIR
Charpy kerbs impact strength RT -30°C	> 28 > 21	kJ/m <sup>2</sup>	EN ISO 179
Dust/undersize	< 0.1	%	< 1 mm
Schüttdichte	> 400	kg/m <sup>3</sup>	

## Disclaimer

This data sheet is intended for your personal use only. Guide values are given in this data sheet. These values can be influenced by processing conditions, modifications, material additives and environmental influences and do not exempt the user from carrying out his own tests and trials. The processing conditions influence the values to a large extent, therefore it is essential to test the material under conditions of use on the finished part. The values are compiled on the basis of current experience and knowledge. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information. We reserve the right to change these values without prior notice. The recipient of our products is responsible for complying with all regulations.

## Contact

### PB Solutions GmbH

Talstraße 74	+49 (0)7084 92 73 523
75328 Schömberg	+49 (0)7084 92 73 522
<a href="http://www.pbs-recycling.de">www.pbs-recycling.de</a>	<a href="mailto:info@pbs-recycling.de">info@pbs-recycling.de</a>