



Material data sheet – PS (C383)

General technical data

Type of material	Polycarbonate
Description	light coloured recycle
Origin	ex MedTech

Physical/mechanical properties

	Value	Unit	Test method
Purity	> 99.9	%	DFA, MIR
Dust/undersize	< 0.1	%	
Grain size	< 8.0	mm	EN ISO 3310
Tensile strength	39.1	Mpa	EN ISO 527-1/2
E-module	3022	Mpa	
Charpy kerbs impact strength	22.3/1.1*	kJ/m ²	EN ISO 179-1
Residual moisture	< 0.2	%	EN ISO 15512
Density	1.04	g/cm ³	EN ISO 1183
MFI (200 °C/5 kg)	7 – 11	g/10 min	EN ISO 1133
MFI string	even, coloured string		

* without/with kerbs RT

Photo documentation



MFI strings



Recyclate

Disclaimer

This data sheet is intended for your personal use only. Guide values are given in this data sheet. These values can be influenced by processing conditions, modifications, material additives and environmental influences and do not exempt the user from carrying out his own tests and trials. The processing conditions influence the values to a large extent, therefore it is essential to test the material under conditions of use on the finished part. The values are compiled on the basis of current experience and knowledge. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information. We reserve the right to change these values without prior notice. The recipient of our products is responsible for complying with all regulations.

PB Solutions GmbH

Talstraße 74

75328 Schöenberg

www.pbs-recycling.de

+49 (0)7084 92 73 523

+49 (0)7084 92 73 522

info@pbs-recycling.de